

KYOTO

Porcelain

PIEDRA | PORCELÁNICO ESMALTADO  
STONE | GLAZED PORCELAIN TILES  
PIERRE | GRÉS CERAME EMAILLÉ  
STEIN | GLASIERTES FEINSTEINZEUG  
КАМЕНЬ | КЕРАМОГРАНИТ ГЛАЗУРОВАННЫЙ

60x60 cm / 24"x24"



G8832 Kyoto Beige 60x60 / 24"x24"



G8832 Kyoto Beige 60x60 / 24"x24"



G8831 Kyoto Gray 60x60 / 24"x24"



G8830 Kyoto White 60x60 / 24"x24"

60x60 cm / 24"x24"




G8830 Kyoto White  
60x60 cm / 24"x24"



G8831 Kyoto Gray  
60x60 cm / 24"x24"



G8832 Kyoto Beige  
60x60 cm / 24"x24"



CARACTERÍSTICAS TÉCNICAS  
TECHNICAL DATA  
CARACTÉRISTIQUES TECHNIQUES  
TECHNISCHE CHARAKTERISTIKEN  
ТЕХНИЧЕСКАЯ ХАРАКТЕРИСТИКА

COLOR COLOUR	FLEXIÓN BENDING ISO-10545-4	DUREZA HARDNESS MOHS/EN-101	ABRASIÓN-PEI ABRASION-PEI ISO-10545-7	CUARTEO CRAZING ISO-10545-11	RESISTENCIA AL ATAQUE QUÍMICO CHEMICAL ATTACK RESISTANCE				R. HELADA FROST RESISTANCE ISO-10545-12	DESIZAMIENTO SLIP RESISTANCE DIN 51130-R	DESIZAMIENTO SLIP RESISTANCE UNE-ENV 12633	DCOF ANSI A137.1	CLASIFICACIÓN GROUP Giorbello
					MANCHAS STAINS	AG. LIMPIEZA CLEANING AG.	DOT. POOL ADDIT.	ACIDOS/BASES ACIDS/BASES					
KYOTO WHITE	≥ 35	5	IV	CUMPLE	5	A	A	LA/HA	CUMPLE	R-9	C1	0,42 ≤ DCOF < 0,60	W
KYOTO GRAY	≥ 35	5	IV	CUMPLE	5	A	A	LA/HA	CUMPLE	R-9	C1	0,42 ≤ DCOF < 0,60	W
KYOTO BEIGE	≥ 35	5	IV	CUMPLE	5	A	A	LA/HA	CUMPLE	R-9	C1	0,42 ≤ DCOF < 0,60	W

DESARROLLO GRÁFICO  
GRAPHIC DEVELOPMENT  
DÉVELOPPEMENT GRAPHIQUE  
GRAFISCHE VIELFALT  
ГРАФИЧЕСКОЕ РАЗВИТИЕ

60x60 / 12 patterns

PACKING LIST

FORMATO SIZE	ESPESOR THICKNESS	ARTÍCULO ARTICLE	PZS / CJ PCS / BOX	FT2 / CJ SQFT / BOX	CJ / PAL BOX / PAL	FT2 / PAL SQFT / PAL	LBS / PZA LBS / PIECE	LBS / CJ LBS / BOX	LBS / FT2 LBS / SQFT	LBS / PAL LBS / PAL
60x60	9.5	Kyoto	4	15.28	5	76.40	15.77	63.07	4.13	315.35